Issue date: June-2024
Version: v02

BIO-HOOPOL 11034

DESCRIPTION

BIO-HOOPOL 11034 is a bio-based linear polyester polyol with an average molecular weight of 3750.

RENEWABLE CONTENT

Recycled PET*	21	%
Bio-based Carbon content**	64	%

*Based on ISO 14021:2021. Minimum content
**ASTM 6866-20 (as theoretical calculation). Minimum content

APPLICATIONS

- Reactive Hot-Melts

TYPICAL PROPERTIES

Appearance	Liquid	
Glass Transition (DSC)	-17	°C
Hydroxyl Nr.	27-34	mg KOH/g
Acid value	≤2,0	mg KOH/g
Viscosity at 120°C	1.000-5.000	mPa.s
Water content	≤0,1	%

HMPUR TYPICAL DATA

BIO-HOOPOL 11034 reacted with MDI at a ratio OH:NCO 1:2,2.

Viscosity at 130°C	10.000	mPa.s
Open time	Sv*	s
Setting time	Sv*	s
Tensile strength	14	N/mm2
Elongation at break	600	%

*Sv: Several hours


This technical information is, to the best of our knowledge and experience, accurate at the time of publication. Nothing herein is to be constructed as a warranty, express or otherwise. It is the responsibility of recipient to test the suitability of our products for their own purpose, as individual conditions of storage, use, and application, as well as suggested formulations and recommendations, are beyond our control. It is the responsibility of the recipient of our products to ensure that applicable property rights, laws and legislation are observed. The information and data contained herein merely serve as general information, do not constitute sales specifications and may be updated without notice. To ensure you are viewing the most recent and accurate product information, visit www.synthesia.com/products/Bio-Hoopol_11034 or contact cservice@synthesia.com

Synthesia Technology Europe Tel. +34 936 821 300 | cservice@synthesia.com | infoeurope@synthesia.com
Synthesia Technology America Tel. +507 430 9702 | cservice_pma@synthesia.com | infoamerica@synthesia.com

Issue date: June-2024
Version: v02

BIO-HOOPOL 11034

VISCOSITY CURVE



STORAGE RECOMMENDATIONS

BIO-HOOPOL 11034 properties could be altered in contact with water. Under normal storage conditions, the product has a shelf-life of at least 24 months. Keep drums or containers tightly closed.

Eventually, the polyester may crystallize. The crystallized product disappears by heating the polyester at 60ºC until a homogeneous material is obtained.

SAFETY RECOMMENDATIONS

Please check the latest version of product´s Safety Data Sheet (SDS) before using the product.

SUPPLY FORM

Please check with our Customer Service or Sales Representative the different supply formats.

This technical information is, to the best of our knowledge and experience, accurate at the time of publication. Nothing herein is to be constructed as a warranty, express or otherwise. It is the responsibility of recipient to test the suitability of our products for their own purpose, as individual conditions of storage, use, and application, as well as suggested formulations and recommendations, are beyond our control. It is the responsibility of the recipient of our products to ensure that applicable property rights, laws and legislation are observed. The information and data contained herein merely serve as general information, do not constitute sales specifications and may be updated without notice. To ensure you are viewing the most recent and accurate product information, visit www.synthesia.com/products/Bio-Hoopol_11034 or contact cservice@synthesia.com

Synthesia Technology Europe Tel. +34 936 821 300 | cservice@synthesia.com | infoeurope@synthesia.com
Synthesia Technology America Tel. +507 430 9702 | cservice_pma@synthesia.com | infoamerica@synthesia.com